

JP 08-003203 A

(c) 2003 Thomson Derwent. All rts. reserv.

010597256

WPI Acc No: 1996-094209/ 199610

Prepn. of polyethylene-alpha-polyolefin copolymer with increased productivity - by copolymerising ethylene@ and alpha-olefin, dividing inside of reactor into chambers and supplying metallocene catalyst and Ziegler catalyst

Patent Assignee: TOSOH CORP (TOYJ)

Number of Countries: 001 Number of Patents: 001

Patent Family:

Patent No	Kind	Date	Applicat No	Kind	Date	Week
JP 8003203	A	19960109	JP 94137038	A	19940620	199610 B

Priority Applications (No Type Date): JP 94137038 A 19940620

Patent Details:

Patent No Kind Lan Pg Main IPC Filing Notes

JP 8003203 A 9 C08F-002/04

Abstract (Basic): JP 8003203 A

Prepn. of an ethylene/alpha-olefin copolymer comprises copolymerising ethylene and a 3 or more C alpha-olefin with the inside of a reactor divided into at least three chambers, supplying a metallocene catalyst to an upper chamber in the reactor and supplying a Ziegler type catalyst to a lower chamber in the reactor.

USE - Used for the prepn. of an ethylene/3+ C copolymer.

ADVANTAGE - The process increases the productivity of the copolymer while maintaining copolymer characteristics.

Dwg.0/1

Derwent Class: A17; E12

International Patent Class (Main): C08F-002/04

International Patent Class (Additional): C08F-004/642; C08F-210/16